


PEROXAN A-40 KP

Ketone peroxide / Curing

Description

Mixture of tert-Butyl peroxybenzoate and Acetylacetone peroxide
Solution in diacetone alcohol

PEROXAN A-40 KP is used for the curing of unsaturated polyester resins.



CAS No.:

614-45-9; 37187-22-7

Technical data

Appearance:

clear liquid

Active oxygen assay:

appx. 4.5%

Density at 20°C:

1.08 g/cm³

Solubility

Insoluble in water, soluble in various organic solvents

Storage

Maximum storage temperature (Ts max):

25°C

Minimum storage temperature (Ts min):

5°C um Kristallisation zu verhindern

Storage stability as from date of delivery:

6 months

Hazardous reactions

Keep packaging tightly closed in a well ventilated place at indicated storage temperature. Keep away from reducing agents e.g. amines, acids, alkalis, heavy metal compounds (e.g. accelerators, driers, metal soaps). Never weigh out in storage room.

Oxidizing agent. Decomposes violently under the influence of heat or by contact with reducing agent. Never mix with accelerators.

Safety characteristics

Flash point:

65°C

SADT:

60°C

The SADT (Self Accelerating Decomposition Temperature) is the lowest temperature at which a self accelerating decomposition may occur.

PEROXAN A-40 KP

Ketone peroxide / Curing

Application

PEROXAN A-40 KP is used for the curing of unsaturated polyester resins in combination with a cobalt accelerator e.g. PERGAQUICK C12 X at ambient and elevated temperatures.

Applications areas for the cure system PEROXAN A-40 KP plus a cobalt accelerator can be e.g. continuous laminating, resin transfer moulding and filament winding.

Depending on application and working conditions, the following peroxide and when applicable cobalt accelerator dosage levels are recommended:

PEROXAN A-40 KP: 1,0 to 2,0 phr

PERGAQUICK C12 X (Cobalt, 1%): 0,5 to 1,0 phr

Packaging

25kg container

Major decomposition products

Acetone, acetylacetone, Benzoic acid, Benzene, , Carbon dioxide, Methane, mixture of aliphatic acids, tert-Butanol, Water

Safety and handling

Please refer to the material safety data sheet (MSDS) for information concerning safe storage, use and handling of PEROXAN A-40 KP. This information should be thoroughly reviewed prior to acceptance of this product. The MSDS is available for downloading at www.pergan.com or through contacting Pergan directly.

The information presented herein is true and accurate and to the best of our knowledge, but without any guarantee. Since the conditions of use are beyond our control we disclaim any liability, including for patent infringement, incurred in connection with the use of these products, data or suggestions.