


PEROXAN APO

Peroxyester / Polymerization

Description

tert-Amyl peroxy-2-ethylhexanoate
95%, Liquid

PEROXAN APO is used for the (co)polymerization of ethylene, styrene, acrylonitrile, acrylates and methacrylates.



Molecular weight: **230.4**
CAS No.: **686-31-7**

Technical data

Appearance: **clear liquid**
Peroxide assay: **min. 95%**
Active oxygen assay: **min. 6.6%**
Density at 20°C: **0.9 g/cm³**

Half life time

in chlorobenzene:

t _{1/2}	10h	1h	1min
bei	73°C	91°C	128°C

Storage

Maximum storage temperature (Ts max): **5°C**
Storage stability as from date of delivery: **3 months**

Hazardous reactions

Organic Peroxides are more or less stable products but will decompose under the influence of heat. To minimize a loss of quality during storage, it is important that the recommended maximum storage temperature is not exceeded. If a minimum storage temperature is given, an undesirable process such as a solidification or phase separation, is known to occur below this temperature.

Safety characteristics

SADT: **35°C**
Emergency temperature: **25°C**
Control temperature: **20°C**

The SADT (Self Accelerating Decomposition Temperature) is the lowest temperature at which a self accelerating decomposition may occur.

The emergency temperature is derived from the SADT. It is the temperature at which emergency actions have to be taken. The control temperature is the maximum temperature at which the product can be transported safely.

PEROXAN APO

Peroxyester / Polymerization

Application

Polymerization of ethylene:

PEROXAN APO is used for high pressure polymerization of ethylene in both autoclave and tubular processes, usually in combination with other peroxides of varying degrees of activity.

Temperature range: 160 to 210°C

Light-off temperature at 2300 bar: 184°C

Polymerization of styrene:

PEROXAN APO may be used in polymerization and copolymerization of styrene.

Temperature range: 80 to 110°C

Dosing: 0,1 to 0,5 phr

Polymerization of acrylates and methacrylates:

PEROXAN APO can be used as initiator for the solution, bulk and suspension (co)polymerization of acrylates and methacrylates.

Temperature range (solution polym.): 70 to 120°C

Dosing: 0,1 to 1 phr

Other applications:

PEROXAN APO may also be used for the (co)polymerization of acrylonitrile.

Packaging

25kg container

Major decomposition products

3-(1,1-Dimethylpropoxy)heptane, Acetone, Ethane, Heptane, Carbon dioxide, Methane, tert Amyl-alcohol

Safety and handling

Please refer to the material safety data sheet (MSDS) for information concerning safe storage, use and handling of PEROXAN APO. This information should be thoroughly reviewed prior to acceptance of this product. The MSDS is available for downloading at www.pergan.com or through contacting Pergan directly.

The information presented herein is true and accurate and to the best of our knowledge, but without any guarantee. Since the conditions of use are beyond our control we disclaim any liability, including for patent infringement, incurred in connection with the use of these products, data or suggestions.