


PEROXAN BIB-1

Dialkyl peroxide / Crosslinking

Description Di-(2-tert.-butyl-peroxyisopropyl)-benzene
95%, Powder

PEROXAN BIB-1 is used for the crosslinking of natural rubber and synthetic rubber, as well as polyolefins.



Molecular weight: **338.5**
CAS No.: **25155-25-3**

Technical data Appearance: **white powder**
Peroxide assay: **min. 95%**
Active oxygen assay: **min. 8.98%**
Bulk density at 20°C: **561 kg/m³**

Half life time in an EPDM compound:

t _{1/2}	10h	1h	1min
bei	117°C	146°C	169°C

Solubility Insoluble in water, Soluble in aromatic and aliphatic solvents, ketones

Storage Maximum storage temperature (Ts max): **30°C**
Storage stability as from date of delivery: **6 months**

Hazardous reactions Keep packaging tightly closed in a well ventilated place at indicated storage temperature. Keep away from reducing agents e.g. amines, acids, alkalis, heavy metal compounds (e.g. accelerators, driers, metal soaps). Never weigh out in storage room.

Oxidizing agent. Decomposes violently under the influence of heat or by contact with reducing agent. Never mix with accelerators.

Organic Peroxides are more or less stable products but will decompose under the influence of heat. To minimize a loss of quality during storage, it is important that the recommended maximum storage temperature is not exceeded. If a minimum storage temperature is given, an undesirable process such as a solidification or phase separation, is known to occur below this temperature.

Safety characteristics Flash point: **>SADT°C**
SADT: **80°C**

The SADT (Self Accelerating Decomposition Temperature) is the lowest temperature at which a self accelerating decomposition may occur.

PEROXAN BIB-1

Dialkyl peroxide / Crosslinking

Application

PEROXAN BIB-1 is recommended for the crosslinking of NBR, SBR, EP(D)M, LDPE and EVA. Rubber compounds containing PEROXAN BIB-1 have excellent scorch safety.

Safe processing temperature (t2): 135°C
Typical crosslinking temperature (t90): 175°C

The safe processing temperature t2 is defined as the temperature, at which the scorch time is longer than 20 minutes.

The typical crosslinking temperature t90 is defined as the temperature at which 90% of the crosslinks in the compound are formed within about 12 minutes.

Packaging

20kg cardboard box

Major decomposition products

Acetone, Acetyl-2-hydroxyisopropylbenzene, Di(2-hydroxyisopropyl)benzene, Diacetylbenzene, Methane, tert-Butanol

Safety and handling

Please refer to the material safety data sheet (MSDS) for information concerning safe storage, use and handling of PEROXAN BIB-1. This information should be thoroughly reviewed prior to acceptance of this product. The MSDS is available for downloading at www.pergan.com or through contacting Pergan directly.

The information presented herein is true and accurate and to the best of our knowledge, but without any guarantee. Since the conditions of use are beyond our control we disclaim any liability, including for patent infringement, incurred in connection with the use of these products, data or suggestions.