


PEROXAN CU-90 L

Hydroperoxide / Polymerization

Description

Cumyl hydroperoxide
90%, Solution in cumene

PEROXAN CU-90 L is used for the copolymerization of styrene/butadiene (SBR rubber) and acryl nitrile/butadiene/styrene (ABS rubber) as well as for the emulsion polymerization of (meth-)acrylates and acrylic resins dispersions.



Molecular weight:

152.2

CAS No.:

80-15-9

Technical data

Appearance:

clear, colourless or light yellow liquid

Peroxide assay:

appx. 90%

Active oxygen assay:

appx. 9.46%

Density at 20°C:

1.06 g/cm³

Half life time

in chlorobenzene:

t _{1/2}	10h	1h	1min
bei	140°C	166°C	222°C

Storage

Maximum storage temperature (Ts max):

30°C

Minimum storage temperature (Ts min):

0°C

Storage stability as from date of delivery:

6 months

Hazardous reactions

Organic Peroxides are more or less stable products but will decompose under the influence of heat. To minimize a loss of quality during storage, it is important that the recommended maximum storage temperature is not exceeded. If a minimum storage temperature is given, an undesirable process such as a solidification or phase separation, is known to occur below this temperature.

Safety characteristics

SADT:

70°C

The SADT (Self Accelerating Decomposition Temperature) is the lowest temperature at which a self accelerating decomposition may occur.

PEROXAN CU-90 L

Hydroperoxide / Polymerization

Application

Copolymerization of styrene/butadiene (SBR rubber) and acryl nitrile/ butadiene/styrene (ABS rubber):

The emulsion polymerization can be initiated through a redox mechanism at low temperatures. Suitable reducing agents are Fe-salts, sulphites, dithionites, etc.

Temperature range: 5 to 20°C

Dosing: 0,1 to 0,3 phr

Polymerization of (meth-)acrylates and acrylic resins dispersions:

The emulsion polymerization can be initiated through a redox mechanism at low temperatures. Suitable reducing agents are Fe-salts, sulphites, dithionites, ascorbinic acid or sugar, etc.

Temperature range: 50 to 80°C

Dosing: 0,1 to 0,5 phr

Packaging

25kg container

200kg drum

Major decomposition products

2-Phenylisopropanol, acetophenone, Methane

Safety and handling

Please refer to the material safety data sheet (MSDS) for information concerning safe storage, use and handling of PEROXAN CU-90 L. This information should be thoroughly reviewed prior to acceptance of this product. The MSDS is available for downloading at www.pergan.com or through contacting Pergan directly.

The information presented herein is true and accurate and to the best of our knowledge, but without any guarantee. Since the conditions of use are beyond our control we disclaim any liability, including for patent infringement, incurred in connection with the use of these products, data or suggestions.