


# PEROXAN LP-40 W

## Diacyl peroxides / Polymerization

### Description

Dilauroyl peroxide  
40%, Suspension in water

PEROXAN LP-40 W is used for the (co)polymerization of vinylchloride, vinylidenchloride, acrylates and methacrylates.



Molecular weight:

**398.6**

CAS No.:

**105-74-8**

### Technical data

Appearance:

**white suspension**

Peroxide assay:

**appx. 40%**

Active oxygen assay:

**appx. 1.61%**

Density at 20°C:

**1 g/cm<sup>3</sup>**

### Half life time

in chlorobenzene:

$t_{1/2}$	10h	1h	1min
bei	<b>61°C</b>	<b>79°C</b>	<b>117°C</b>

### Storage

Maximum storage temperature (Ts max):

**30°C**

Minimum storage temperature (Ts min):

**5°C** to prevent freezing

Storage stability as from date of delivery:

**3 months**

### Hazardous reactions

Organic Peroxides are more or less stable products but will decompose under the influence of heat. To minimize a loss of quality during storage, it is important that the recommended maximum storage temperature is not exceeded. If a minimum storage temperature is given, an undesirable process such as a solidification or phase separation, is known to occur below this temperature.

### Safety characteristics

SADT:

**50°C**

SADT in IBC:

**50°C**

The SADT (Self Accelerating Decomposition Temperature) is the lowest temperature at which a self accelerating decomposition may occur.

# PEROXAN LP-40 W

## Diacyl peroxides / Polymerization

---

### Application

Polymerization of vinylchloride:

PEROXAN LP-40 W may be used in suspension polymerization of vinylchloride. Very often, PEROXAN LP-40 W is combined with a more active initiator such as a peroxydicarbonate to increase reactor efficiency.

Reasons to use a water based peroxide suspension are the following:

- Enhanced safety
- Solvent free. No contamination of the VCM recycle stream
- Enhancement of PVC purity
- Easy to use (pumpable) in "closed reactor technology"
- Easy to dilute with water

PEROXAN LP-40 W is especially suitable for the production of micro-S-PVC.

Temperature range: 50 to 70°C

Dosing: 0,2 to 0,8 phr

Polymerization of acrylates and methacrylates:

PEROXAN LP-40 W can be used as initiator for the polymerization of acrylates and methacrylates as a replacement for 2,2'-Azobis(isobutyronitril) (PEROXAN AZDN).

Temperature range: 60 to 90°C

Dosing: 0,2 to 0,8 phr

Other applications:

PEROXAN LP-40 W may also be used for the polymerization of vinylidenchloride.

### Packaging

**25kg container**

**900kg IBC**

Bulk delivery of PEROXAN LP-40 W in a 1,00 m<sup>3</sup> plastic intermediate bulk container (IBC) is possible in a number of countries.

### Major decomposition products

**Docosane, Carbon dioxide, Undecane, Undecyl dodecanoate**

### Safety and handling

Please refer to the material safety data sheet (MSDS) for information concerning safe storage, use and handling of PEROXAN LP-40 W. This information should be thoroughly reviewed prior to acceptance of this product. The MSDS is available for downloading at [www.pergan.com](http://www.pergan.com) or through contacting Pergan directly.

The information presented herein is true and accurate and to the best of our knowledge, but without any guarantee. Since the conditions of use are beyond our control we disclaim any liability, including for patent infringement, incurred in connection with the use of these products, data or suggestions.