

PEROXAN ME-30 LX

Ketone peroxide / Curing

Description Methyl ethyl ketone peroxide

Solution in TXIB

PEROXAN ME-30 LX is a general purpose MEKP used for the curing of unsaturated polyester at ambient temperature in combination with cobalt accelerators.

CAS No.: 1338-23-4

Technical data Appearance: clear liquid

Active oxygen assay: appx. 7.7%

Density at 20°C: 0.995 g/cm³

Solubility Insoluble in water

Storage Maximum storage temperature (Ts max): 30°C

Minimum storage temperature (Ts min): 0°C
Storage stability as from date of delivery: 6 months

Hazardous reactions Keep packaging tightly closed in a well ventilated place at indicated storage temperature. Keep away from

reducing agents e.g. amines, acids, alkalis, heavy metal compounds (e.g. accelerators, driers, metal soaps).

Never weigh out in storage room.

Oxidizing agent. Decomposes violently under the influence of heat or by contact with reducing agent. Never mix

with accelerators.

Safety characteristics Flash point: 44°C

SADT: 60°C

The SADT (Self Accelerating Decomposition Temperature) is the lowest temperature at which a self accelerating decomposition may occur.





PEROXAN ME-30 LX

Ketone peroxide / Curing

Application

PEROXAN ME-30 LX is used for the curing of unsaturated polyester resins at ambient temperature in combination with cobalt accelerators.

PEROXAN ME-30 LX is a lower concentrated version of PEROXAN ME-50 LX and is especially developed for spray-up applications when a more accurate dosing is required. The curing system PEROXAN ME-30 LX and Cobalt accelerator is particularly suitable for the curing of gel coat resins and laminating resins; moreover the manufacture of light resistant parts may be possible contrary to the curing system Benzoyl peroxide and Amine accelerator.

Depending on working conditions, the following peroxide and accelerator dosage levels are recommended:

PEROXAN ME-30 LX: 1,5 to 4,0 phr

PERGAQUICK C12 X (Cobalt, 1%): 0,5 to 3,0 phr

Packaging 30kg container

Major decomposition products Formic acid, Acetic acid, Carbon dioxide, Methylethylketon, Propionic acid, Water

Safety and handling

Please refer to the material safety data sheet (MSDS) for information concerning safe storage, use and handling
of PEROXAN ME-30 LX. This information should be thoroughly reviewed prior to acceptance of this product.

The MSDS is available for downloading at www.pergan.com or through contacting Pergan directly.

The information presented herein is true and accurate and to the best of our knowledge, but without any guarantee. Since the conditions of use are beyond our control we disclaim any liability, including for patent infringement, incurred in connection with the use of these products, data or suggestions.

