


PEROXAN PK122 V-80

Peroxyketale / Curing

Description

1,1-Di-(tert-butylperoxy)-cyclohexane
80%, Solution in odorless white spirits

PEROXAN PK122 V-80 is used for the curing of unsaturated polyester resins.



Molecular weight: **260.4**
CAS No.: **3006-86-8**

Technical data

Appearance: **clear liquid**
Peroxide assay: **appx. 80%**
Active oxygen assay: **appx. 9.83%**
Density at 20°C: **0.88 g/cm³**

Storage

Maximum storage temperature (Ts max): **25°C**
Storage stability as from date of delivery: **6 months**

Hazardous reactions

Keep packaging tightly closed in a well ventilated place at indicated storage temperature. Keep away from reducing agents e.g. amines, acids, alkalis, heavy metal compounds (e.g. accelerators, driers, metal soaps). Never weigh out in storage room.

Oxidizing agent. Decomposes violently under the influence of heat or by contact with reducing agent. Never mix with accelerators.

Organic Peroxides are more or less stable products but will decompose under the influence of heat. To minimize a loss of quality during storage, it is important that the recommended maximum storage temperature is not exceeded. If a minimum storage temperature is given, an undesirable process such as a solidification or phase separation, is known to occur below this temperature.

Safety characteristics

SADT: **60°C**

The SADT (Self Accelerating Decomposition Temperature) is the lowest temperature at which a self accelerating decomposition may occur.

PEROXAN PK122 V-80

Peroxyketale / Curing

Application

PEROXAN PK122 V-80 is used for the curing of unsaturated polyester resins at elevated temperatures.

PEROXAN PK122 V-80 is preferred for the curing of UP resin based hot press moulding formulations in the temperature range from 120° to 170°C.

The stability of this peroxyketal in an UP resin is hardly influenced by the presence of metal accelerators, pigments or fillers. PEROXAN PK122 V-80 is therefore very suitable for pigmented and non-pigmented hot press moulding formulations where a long shelf life of the compound is required.

Depending on working conditions, the following peroxide dosage level is recommended:

PEROXAN PK122 V-80: 1,5 to 2,5 phr

Packaging

20kg container

Major decomposition products

Acetone, Hexanoic acid, Carbon dioxide, Methane, tert-Butanol

Safety and handling

Please refer to the material safety data sheet (MSDS) for information concerning safe storage, use and handling of PEROXAN PK122 V-80. This information should be thoroughly reviewed prior to acceptance of this product. The MSDS is available for downloading at www.pergan.com or through contacting Pergan directly.

The information presented herein is true and accurate and to the best of our knowledge, but without any guarantee. Since the conditions of use are beyond our control we disclaim any liability, including for patent infringement, incurred in connection with the use of these products, data or suggestions.